COMPAKTUNA®

PASTAFIX T

Ready-to-use flexible tile adhesive

CE
13

COMPAKTUNA® bv/srl
INDUSTRIEPARK ZWIJNAARDE 6
9052 GENT – BELGIUM
1136

103/CPR/130701

EN 12004 + A1:2012

PASTAFIX T

Dispersion adhesive/floors and walls/internal and external

Bond strength as:	
- Initial shear adhesion strength	≥ 1 N/mm²
Shear adhesion strength:	
- After heat ageing	≥ 1 N/mm²
- At elevated temperature	≥ 1 N/mm²
- After water immersion	≥ 0,5 N/mm²














CHARACTERISTICS

PASTAFIX T is a ready-to-use, non-slip paste adhesive that allows easy bonding of faience, ceramics, glass mosaic, stone strips, natural stone, etc. to a flat and clean surface. Suitable surfaces are: concrete, masonry, plasterwork, cement work, cellular concrete, wood chipboard, plasterboard, veneer panels and coated extruded PS panels.

Due to its studied composition, PASTAFIX T provides much better adhesion than with ordinary mortar. Thin layer installations are possible. With PASTAFIX T, you never have any surplus or waste and the wetting of the tiles and the substrate is also eliminated.

PASTAFIX T is a waterproof tile adhesive that can be used both indoors and outdoors. PASTAFIX T is suitable for applications in “wet areas” such as showers, bathrooms, kitchens, etc. PASTAFIX T may not be used in a permanently humid environment (e.g. swimming pools). In such cases, we can recommend our products FLEXcement® (PLUS, PREMIUM, COMFORT).

PASTAFIX T shows no signs of aging after setting, is insensitive to frost and provides a permanent elastic bond.

Technical characteristics	Meets the requirement according to NBN EN 12004 MPa (N/mm²)
Initial sliding resistance (D2)	≥ 1
Adhesion after immersion in water (D2)	≥ 0,5
Adhesion after aging at +70 °C (D2)	≥ 1
Adhesion at +70 °C (D2)	≥ 1
Adhesion after open time of 30 minutes (E)	≥ 0,5
Vertical sliding resistance (T)	≤ 0,5 mm

Mixing ratio	Consumption	Packaging
Undiluted	±1 to 1,5 kg/mm/m²	2 kg (12 pc/carton), 8 kg and 15 kg
Colour	**Open time**	**Application temperature**
White	> 20 min	+10 °C to +30°C

PASTAFIX T

DIRECTIONS FOR USE

PASTAFIX T is always applied to a clean, healthy, dust- and oil-free substrate. Panels used as substrates must always be firmly attached. Apply the adhesive in a thin layer (4 to 10 mm adhesive comb) to the surface with a notched trowel or trowel, and immediately ensure even distribution with a notched trowel. Then press the dry tiles with a small rotating movement.





REMARKS

- The tiles must be placed 30 minutes after applying the adhesive.
- The grouting of the tiles with grout is done after the adhesive has dried. See our products JOINT HY, JOINT BREED SP and EPOXY-JOINT RG.
- Setting time: wait at least 24 hours before grouting. When gluing full ceramic tiles, wait at least 48 hours.
- The full curing time is approximately 7 days at +23°C and 50% relative humidity.
- Setting and reaching the final strength of the adhesive depend on temperature, relative humidity, type of substrate and type of tile.
- The tools are cleaned with water immediately after use so that the adhesive cannot dry out.
- If the tiles sag slightly due to their weight, use suitable spacers.



PACKAGING

Shelf life is 12 months, in unopened packaging. Close opened packaging well after use. Store frost-free. Available in 2 kg, 8 kg and 15 kg.



20240122

As the applications of our products are diverse, no single application guideline can be laid down. All product data refl ect the state of knowledge of our products at the time of publication. Therefore all suggestions and recommendations concerning the use of our products are merely illustrative. Apply the product on a small and insignifi cant spot before starting to use our products to be sure the desired result is obtained. Always ask for the technical sheet of our products. Visit the website www.compaktuna.be. Consult our “technical department” which can be reached for free on the green number 0800/92279. The Dutch text shall be exclusively binding.
Version 10/02/2014. **COMPAKTUNA BV is EN ISO 9001 certified.**

COMPAKTUNA®
Quality & Innovation

A MEMBER OF HOLCIM GROUP

COMPAKTUNA bv/srl
Industriepark III
Industriepark Zwijnaarde 6
9052 Gent - Belgium
T +32 9 221 11 16
VAT BE0400.166.768 - R.P.R. Gent
info@compaktuna.be
www.compaktuna.be