COMPAKTUNA®

GEDROOGD KWARTSZAND

White, dried sand

TYPE 1 & TYPE 2



CHARACTERISTICS

This DRIED QUARTZ SAND has the following main properties:

- very high purity
- uniform
- does not stain
- hard
- easily workable, e.g., flows smoothly into gaps
- absorbs little water
- does not contaminate
- contains no organic matter or clay
- ecological

White sand that consists of 99.5% silicon sand

Technical characteristics	Measured values
Soortelijk gewicht = Specific gravity	2,65
Stortgewicht = Bulk density	1,5
Hardheid = Hardness	7 (Mohs scale)
Gehalte SiO2 = SiO2 content (Silicon dioxide content)	99,50%
Gehalte Fe2O3 = Fe2O3 content (Iron oxide content)	0,03%

Grain size	Type 1	Type 2
> 0,50 mm	25%	0%
> 0,25 mm	85%	57%
> 0,18 mm	98%	93%

GEDROOGD KWARTSZAND TYPE 1 & TYPE 2

APPLICATION

Joint sand
For jointing paving, driveways, terraces, floors, etc. The sand easily fills all gaps and cracks, and absorbs little water, allowing it to dry quickly after wetting.

Joint mortars
This sand provides a smooth, easy-to-work mortar for joints up to 10 mm, is very hard, increases water resistance, does not stain, and reduces the chance of efflorescence.

Abrasive powder
DRIED QUARTZ SAND is very hard and can be sprinkled under grinding stones as an additional abrasive. This sand type can also be used for wet sandblasting, e.g., for renovating facades, removing old paint layers, moss, algae, etc.

Decorative sand
e.g., in aquariums and terrariums, etc.







PACKAGING

DRIED QUARTZ SAND is available in 25 kg bags. It is available in type 1 and type 2 (type 1 has a coarser grain structure).

20240806

As the applications of our products are diverse, no single application guideline can be laid down. All product data reflect the state of knowledge of our products at the time of publication. Therefore all suggestions and recommendations concerning the use of our products are merely illustrative. Apply the product on a small and insignifi cant spot before starting to use our products to be sure the desired result is obtained. Always ask for the technical sheet of our products. Visit the website www.compaktuna.be. Consult our “technical department” which can be reached for free on the green number 0800/92279. The Dutch text shall be exclusively binding.
Version 10/02/2014. **COMPAKTUNA BV is EN ISO 9001 certified.**

COMPAKTUNA®
Quality & Innovation

A MEMBER OF HOLCIM GROUP

COMPAKTUNA bv/srl
Industriepark III
Industriepark Zwijnaarde 6
9052 Gent - Belgium
T +32 9 221 11 16
VAT BE0400.166.768 - R.P.R. Gent
info@compaktuna.be
www.compaktuna.be