COMPAKTUNA®


SEAL-ALL® XT 8 FLEX

Powerful elastic adhesive sealant and construction joint sealant









CHARACTERISTICS

Ready-to-use adhesive and joint sealant (MS POLYMER) for all kinds of building and construction applications:


- Very good adhesion properties on almost all materials without primer; product is unsuitable for constant water load, aquarium construction, sanitary and dilatation joints; not applicable in combination with PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous surfaces.
- Bonding and sealing with 1 product
- Permanently flexible bond
- High UV and mold resistance
- Shrink-free curing
- Also sticks to wet surfaces and under water
- Fast curing
- Very good workability

Technical characteristics	Measured values
Skin formation at +23 °C and 50% relative humidity	10 minutes
Curing at +23 °C and 50% relative humidity	2 to 3 mm / 24 h.
Volume shrinkage after curing	nil
Hardness - DIN 53505	60 shore A
Tensile strength - DIN 53504	2,20 N/mm²
Thermal stability	-40 °C to 100 °C
Elongation at break - DIN 53504	300%
Contains no isocyanates	non-toxic: odorless, seawater and chlorine resistant, vibration resistant

Curing	Consumption	Packaging
±3 mm/24h	Joints of 10 x 10 mm: ±3 linear meters per tube Joints of 5 x 5 mm: ±12 linear meters per tube	12 tubes of 290 ml per carton
Colour	**Processing time**	**Application temperature**
Grey, white and black	Skin formation after ±10 min.	+5 °C to +40 °C

SEAL-ALL® XT 8 FLEX

APPLICATIONS





- For bonding and sealing metals, plastics, tiles, concrete, glass and wood.
- For the tiler, carpenter, sanitary installer, roofer and fitter.
- Bonding of mirrors.
- Bonding of AFDICHTINGSMAT 290, BINNENHOEK 290, BUITENHOEK 290 and DICHTBAND FLEX.
- Bonding and sealing of oily wood types such as teak.
- Bonding of zinc, aluminium and lead.
- Bonding to polystyrene and PVC.
- Also extremely suitable for difficult applications such as bonding powder-coated metal, EPDM rubber and roofing.
- Suitable for contact with food.

DIRECTIONS FOR USE

- Cut open the tube at the connection and mount the nozzle.
- Cut off the desired opening on the nozzle.
- Use a standard caulking gun or pneumatic caulking gun.
- Apply to a clean and grease-free surface.
- When gluing, apply adhesive strips vertically (ventilating), in ridges, at a distance of min. 10 cm and max. 20 cm. Do not apply in dots.
- To smooth joints, use GLADSTRIJKMIDDEL N.
- Pre-treat highly porous surfaces with SEAL-ALL® PRIMER, non-porous surfaces with SEAL-ALL® CLEANER.

PACKAGING

1 tube contains 290 ml

12 tubes of 290 ml per box

STORAGE TIME

18 months in unopened packaging under normal climatic conditions. Store dry and frost-free.

20250217

As the applications of our products are diverse, no single application guideline can be laid down. All product data refl ect the state of knowledge of our products at the time of publication. Therefore all suggestions and recommendations concerning the use of our products are merely illustrative. Apply the product on a small and insignifi cant spot before starting to use our products to be sure the desired result is obtained. Always ask for the technical sheet of our products. Visit the website www.compaktuna.be. Consult our “technical department” which can be reached for free on the green number 0800/92279. The Dutch text shall be exclusively binding.
Version 10/02/2014. **COMPAKTUNA BV is EN ISO 9001 certified.**

COMPAKTUNA®
Quality & Innovation

A MEMBER OF HOLCIM GROUP

COMPAKTUNA bv/srl
Industriepark III
Industriepark Zwijnaarde 6
9052 Gent - Belgium
T +32 9 221 11 16
VAT BE0400.166.768 - R.P.R. Gent
info@compaktuna.be
www.compaktuna.be